

Trusted global trading company specializing in the procurement and distribution of high-quality oil and petrochemical products

Specification	Value	Test Method
Specific Gravity @ 25/25 deg. C	1.01/1.05	ASTM D.70
Penetration @ 25 deg. C	85/100	ASTM D.5
Softening Point deg. C.	45/52	ASTM D.36
Ductility @ 25 deg. C. CMS	100 min.	ASTM D.113
Loss on heating PCT. WT	0.2 max.	ASTM D.6
Drop in penetration after heating PCT.	20 max.	ASTM D.5
Flash point deg. C.	250 min.	ASTM D.92
Solubility in CS ₂ PCT. WT	99.5 max.	ASTM D.4
Organic matter insoluble in CS ₂ PCT. WT.	0.2 max	ASTM D.4

BITUMEN 85-100

Product description

Hayat Al Majd General Trading Co.

+971 50 895 5353

info@hayatco.co

www.hayatco.co

406, Business Port, Port Saeed, Deira, Dubai